

Temporary CB

A validated material for comfortable, aesthetic temporary restorations

Temporary CB Resin is a Class IIa material designed to 3D print biocompatible dental prosthetics with the Form 3B and Form 2 printers. This tooth-colored resin can print at 50 micron layer line resolutions to produce precisely fitting temporaries with a smooth surface finish, high resolution, and dimensional stability. Restorations made from Temporary CB Resin may remain in the mouth for up to 12 months.

Temporary CB Resin is only validated for use with the Stainless Steel Build Platform.

Temporary Restorations:

Bridges (up to 7 units)

Crowns

Veneers

Onlays

Inlays



FLTCA201
FLTCA301

FLTCB101
FLTCC201

FLTCBL01

* May not be available in all regions

Prepared 06 . 09 . 2020

Rev. 02 25 . 01 . 2022

To the best of our knowledge the information contained herein is accurate. However, Formlabs, Inc. makes no warranty, expressed or implied, regarding the accuracy of these results to be obtained from the use thereof.

MATERIAL PROPERTIES DATA

Temporary CB Resin

VITA¹ CLASSICAL SHADES: A2, A3, B1, C2, BL

	MEASURED VALUES	METHOD
Mechanical Properties		
Density	1.4 - 1.5 g/cm ³	BEGO Standard
Viscosity	2500 - 6000 MPa*s	BEGO Standard
Flexural Strength (post cured) ^{2,3,4}	≥ 100 MPa	EN ISO 10477, EN ISO 4049

Temporary CB Resin is a Medical Device as defined in the Medical Device Directive (93/42/EEC) in the EU and in Section 201(h) of the Federal Food Drug & Cosmetic (FD&C) Act.

Restorations printed with Temporary CB Resin have been evaluated in accordance with ISO 10993-1:2018, Biological evaluation of medical devices - Part 1: Evaluation and testing within a risk management process, and ISO 7405:2009/(R)2015, Dentistry - Evaluation of biocompatibility of medical devices used in dentistry, and passed the requirements for the following biocompatibility risks:

ISO Standard	Description ⁵
EN ISO 10993-5:2009	Not cytotoxic
ISO 10993-10:2010/(R)2014	Not an irritant
ISO 10993-10:2010/(R)2014	Not a sensitizer
ISO 10993-3:2014	Not genotoxic
ISO 10993-1:2009	Non toxic

The product was developed and is in compliance with the following ISO Standards:

ISO Standard	Description
EN ISO 13485:2016	Medical Devices – Quality Management Systems – Requirements for Regulatory Purposes
EN ISO 14971:2019	Medical Devices – Application of Risk Management to Medical Devices

¹ VITA is a registered trademark of a company which is not affiliated with Formlabs Inc.

² Material properties may vary based on part geometry, print orientation, print settings, and environmental conditions.

³ Test samples were printed with a Stainless Steel Build Platform on a Form 2 and Form 3B printer with 50 µm Temporary CB Resin settings. The printed samples were post-processed as recommended in the Instructions for Use.

⁴ Data for post-cured samples were measured on 3 point bending test specimens according to EN ISO 10477 and EN ISO 4049 standards. Screen reader support enabled.

⁵ Temporary CB Resin was tested at Eurofins BioPharma Product Testing, Munich GmbH.